This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS

- TEXT CUT OFF AT TOP, BOTTOM OR SIDES

- FADED TEXT

- ILLEGIBLE TEXT

- SKEWED/SLANTED IMAGES

- COLORED PHOTOS

- BLACK OR VERY BLACK AND WHITE DARK PHOTOS

- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents *will not* correct images, please do not report the images to the Image Problem Mailbox.

PCT

WORLD INTELLEC
Ini

INTERNATIONAL APPLICATION PUBLISHE

(51) International Patent Classification 6 :	A1	(43) International Publication Date: 1 February 1996 (01.02.96)
C03C 13/00		

(21) International Application Number: PCT/GB95/01526

(22) International Filing Date: 30 June 1995 (30.06.95)

(30) Priority Data:
9414154.6   13 July 1994 (13.07.94)   GB

(71) Applicant (for all designated States except US): THE MORGAN CRUCIBLE COMPANY PLC [GB/GB]; Morgan House, Madeira Walk, Windsor, Berkshire SL4 1EP (GB).

(72) Inventor; and
(75) Inventor/Applicant (for US only): JUBB, Gary, Anthony [GB/GB]; 16 Walton Close, Stourport-on-Severn, Worcestershire DY13 8QR (GB).

(74) Agent: PHILLIPS & LEIGH; 7 Staple Inn, Holborn, London WC1V 7QF (GB).

(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG).

Published
With international search report.

(54) Title: SALINE SOLUBLE INORGANIC FIBRES

(57) Abstract

Refractory fibres are disclosed for which a vacuum cast preform of the fibre has a shrinkage of 3.5 % or less when exposed to 1260 °C for 24 hours. The fibres comprise CaO, SiO_2, SrO, and optionally ZrO_2 any incidental impurities amounting to less than 2mol % in total. To achieve the shrinkage performance stated the SiO_2 excess (defined as the amount of SiO_2 calculated as remaining after the above named constituents are crystallised as silicates) exceeds 26 mol %. Preferred fibres comprise:- CaO less than 33.8 mol %, SiO_2 more than 62.1 mol %, and more preferably comprise:- CaO 12.9 to 31.9 mol %, SrO 2.6 to 15.5 mol %, SiO_2 63.2 to 71.3 mol %, ZrO_2 0 to 5.4 mol %.

SALINE SOLUBLE INORGANIC FIBRES

This invention relates to saline soluble, non-metallic, amorphous, inorganic oxide, refractory fibrous materials. The invention particularly relates to glassy fibres having silica as their principal constituent.

Inorganic fibrous materials are well known and widely used for many purposes (e.g. as thermal or acoustic insulation in bulk, mat, or blanket form, as vacuum formed shapes, as vacuum formed boards and papers, and as ropes, yarns or textiles; as a reinforcing fibre for building materials; as a constituent of brake blocks for vehicles). In most of these applications the properties for which inorganic fibrous materials are used require resistance to heat, and often resistance to aggressive chemical environments.

Inorganic fibrous materials can be either glassy or crystalline. Asbestos is an inorganic fibrous material one form of which has been strongly implicated in respiratory disease.

It is still not clear what the causative mechanism is that relates some asbestos with disease but some researchers believe that the mechanism is mechanical and size related. Asbestos of a critical size can pierce cells in the body and so, through long and repeated cell injury, have a bad effect on health. Whether this mechanism is true or not regulatory agencies have indicated a desire to categorise any inorganic fibre product that has a respiratory fraction as hazardous, regardless of whether there is any evidence to support such categorisation. Unfortunately for many of the applications for which inorganic fibres are used, there are no realistic substitutes.

Accordingly there is a demand for inorganic fibres that will pose as little risk as possible (if any) and for which there are objective grounds to believe them safe.

A line of study has proposed that if inorganic fibres were made that were sufficiently soluble in physiological fluids that their residence time in the human body was short; then damage would not occur or at least be minimised. As the risk of asbestos linked disease appears to depend very much on the length of exposure this idea appears reasonable. Asbestos is extremely insoluble.

As intercellular fluid is saline in nature the importance of fibre solubility in saline solution has long been recognised. If fibres are soluble in physiological saline solution then, provided the dissolved components are not toxic, the fibres should be safer than fibres which are not so soluble. The shorter the time a fibre is resident in the body the less damage it can do. H. Förster in 'The behaviour of mineral fibres in physiological solutions' (*Proceedings of 1982 WHO IARC Conference*, Copenhagen, Volume 2, pages 27-55(1988)) discussed the behaviour of commercially produced mineral fibres in physiological saline solutions. Fibres of widely varying solubility were discussed.

International Patent Application No. WO87/05007 disclosed that fibres comprising magnesia, silica, calcia and less than 10 wt% alumina are soluble in saline solution. The solubilities of the fibres disclosed were in terms of parts per million of silicon (extracted from the silica containing material of the fibre) present in a saline solution after 5 hours of exposure. The highest value revealed in the examples had a silicon level of 67 ppm. In contrast, and adjusted to the same regime of measurement, the highest level disclosed in the Förster paper was equivalent to approximately 1 ppm. Conversely if the highest value revealed in the International Patent Application was converted to the same measurement regime as the Förster paper it would have an extraction rate of 901,500 mg Si/kg fibre - i.e. some 69 times higher than any of the fibres Förster tested, and the fibres that had the highest extraction rate in the Förster test were glass fibres which had high alkali contents and so would have a low melting point. This is convincingly better performance even taking into account factors such as differences in test solutions and duration of experiment.

International Patent Application No. WO89/12032 disclosed additional fibres soluble in saline solution and discusses some of the constituents that may be present in such fibres. Among such constituents are ZrO_2 and this document claims (among other things) processes using fibres of composition (in weight %):- ZrO_2 0.06-10%; SiO_2 35-70%; MgO 0-50%; CaO 0-64.5%. However the patent actually discloses a much more limited range of zirconia containing materials.

European Patent Application No. 0399320 disclosed glass fibres having a high physiological solubility.

Further patent specifications disclosing selection of fibres for their saline solubility include for example European 0412878 and 0459897, French 2662687 and 2662688, PCT WO86/04807, WO90/02713, WO92/09536, and WO93/22251, and United States 5250488.

The refractoriness of the fibres disclosed in these various prior art documents varies considerably. The maximum service temperature of any of the above mentioned fibres (when used as refractory insulation) is up to 815°C (1500°F).

Among saline soluble commercial fibres usable at temperatures higher than 815°C are SUPERWOOL ™ a fibre manufactured by The Morgan Crucible Company plc and which has a maximum use temperature of 1050°C and a composition of SiO_2 65wt%; CaO 29wt%; MgO 5wt%; Al_2O_3 1wt%. A similar fibre is INSULFRAX ™ a fibre made by Carborundum Company which has a continuous use limit of 1000°C (1832°F) and which melts at 1260°C (2300°F). This has a composition of SiO_2 65wt%; CaO 31.1wt%; MgO 3.2wt%; Al_2O_3 0.3wt% and Fe_2O_3 0.3wt%.

The applicant's earlier International Patent Application WO93/15028 disclosed saline soluble fibres comprising CaO, MgO and SiO_2 and optionally ZrO_2 usable at temperatures in excess of 1000°C but gave no indication that fibres could be used at still higher temperatures. That same application also discloses methods of predicting the saline solubility of glasses and for screening for the refractoriness of glasses, although whether such glasses can form fibres is a complex function of many characteristics, e.g. viscosity.

In discussing the above mentioned predictive methods International Patent Application WO93/15028 mentions some compositions containing strontium oxide as a constituent but fibres of these compositions were not made.

The applicants have realised that failure of fibres at high temperature occurs primarily upon devitrification of the fibre; if on devitrification insufficient silica is left the fibres will fail through having a shrinkage of greater than 3.5%. Accordingly the applicants have looked to what materials are formed on devitrification and in their earlier International Patent Application No. PCT/GB94/00053 they disclose refractory fibres comprising CaO, SiO_2, MgO, optionally ZrO_2, optionally less than 0.75mol% Al_2O_3 and in which the SiO_2 excess (defined as the amount of SiO_2 calculated as remaining after the above named constituents are crystallised as silicates) exceeds 21.8mol%.

4

The physical basis for the importance of SiO_2 excess may be that it indicates how much silica is left to maintain a glassy phase on crystallisation of the other constituents as silicate materials. Further, the silicate materials that form on devitrification may become liquid or flow at 1260°C so causing shrinkage.

The applicants have found that some systems comprising strontium oxide calcium oxide and silica may form fibres usable at temperatures of up to 1260°C whereas other strontium containing systems do not form such usable fibres. In particular the applicants have found that partial replacement of SrO for MgO in the $CaO/MgO/(ZrO_2)/SiO_2$ fibres of their earlier application PCT/GB94/00053 does not result in success whereas substitution of SrO for MgO tends to give usable fibres.

Accordingly the present invention provides a refractory fibre for which a vacuum cast preform of the fibre has a shrinkage of 3.5% or less when exposed to 1260°C for 24 hours and comprising CaO, SiO_2, SrO, and optionally ZrO_2 any incidental impurities amounting to less than 2mol% in total, and in which the SiO_2 excess (defined as the amount of SiO_2 calculated as remaining after the above named constituents are crystallised as silicates) exceeds 26mol%.

The quantity of potentially fluxing constituents such as alkali metals and other incidental impurities (e.g. iron oxides) should be kept low.

From the compositions tested it appears that preferably the fibre comprises:-

CaO   less than 33.8 mol%
SiO_2 more than 62.1 mol%.

and more preferably comprises:-

CaO   12.9 to 31.9 mol%
SrO   2.6 to 15.5 mol%
SiO_2 63.2 to 71.3 mol%
ZrO_2 0 to 5.4 mol %.

The applicants have investigated, for their saline solubility and refractoriness, a range of fibre compositions. These fibres were formed by blowing the molten constituents from a melt stream in a conventional manner but the invention is not limited to blown fibres and also encompasses fibres formed by spinning or any other means.

Tables 1 & 2 show the results of these tests. Table 1 is divided into the CaO-SrO-ZrO_2-SiO_2 system, the CaO-SrO-SiO_2 system, and some comparative examples (which were never made as fibres). Table 1 indicates for each fibre the linear shrinkages at 800, 1000, 1200, and 1260°C (not all samples measured at every temperature); mole percent composition (based on the constituents CaO, MgO, SrO, ZrO_2, Al_2O_3, TiO_2 and SiO_2); crystalline constituents formed on devitrification (see below); SiO_2 excess (calculation for this figure shown below) and, for the CaO-SrO-SiO_2 fibres and comparative examples, the calculated $CaSiO_3$ to $SrSiO_3$ ratio.   Each sample that has a satisfactory shrinkage of 3.5% or less at 1260°C is indicated by a composition shown in bold. Those compositions that fail to meet the shrinkage criterion are indicated in plain text.

Table 2 shows for the CaO-SrO-ZrO_2-SiO_2 system and the CaO-SrO-SiO_2 system the solubilities (as parts per million) of selected constituents of the fibres in saline solution measured by the method described below and shows the total of the named solubilities. This table is ordered in the same manner as Table 1 for convenient comparison.

3 strontium containing systems were investigated. These are:-

CaO-MgO-SrO-SiO_2
CaO-SrO-SiO_2
CaO-SrO-ZrO_2-SiO_2

In the CaO-MgO-SrO-SiO_2 system very poor results were found - MgO and SrO evidently being incompatible - and so the present invention treats MgO as an incidental impurity that must be held within the 2mol% total given above. The applicants have good reason to believe that the maximum level for MgO may be as low as 1% and preferably the MgO content is kept as low as possible. To some extent therefore SrO may be treated as being in substitution of MgO in the fibres of PCT/GB94/00053.

The CaO-SrO-SiO_2 and CaO-SrO-ZrO_2-SiO_2 systems are discussed separately below.

(1) <u>CaO-SrO-SiO_2</u>

This is a simple system in that only $CaSiO_3$, $SrSiO_3$ and SiO_2 crystallise. Therefore all the CaO forms as $CaSiO_3$ and all the SrO forms as $SrSiO_3$. The resulting excess SiO_2 can then be calculated. However $CaSiO_3$ and $SrSiO_3$ form

a complete solid solution between them, with the melting point being 1580°C for $SrSiO_3$ and 1540°C for $CaSiO_3$, and with a minimum in melting point lying between these extremes. It is reasonable to expect that compositions having significant quantities of both $CaSiO_3$ and $SrSiO_3$ will have lower melting points than either those containing high $CaSiO_3$ and low $SrSiO_3$, or those containing high $SrSiO_3$ and low $CaSiO_3$ contents. Table 1 shows that for those fibres with a $CaSiO_3/SrSiO_3$ ratio of greater than 2 (those fibres lying below line "A") a silica excess of greater than 26mol% neatly divides the workable fibres (having preform shrinkages of less than 3.5% and shown in bold) from those that are not. For those fibres above line "A" where the $CaSiO_3/SrSiO_3$ ratio is less than 2 a silica excess of 34mol% is required to divide the workable from the unworkable compositions. However the applicants suspect that there will be a lower limit (perhaps around $CaSiO_3/SrSiO_3$ ratio 0.5) below which a lower silica excess will prevail again.

(2) $CaO-SrO-ZrO_2-SiO_2$

This is a more complicated system than the $CaO-SrO-SiO_2$ system, with at least 5 components crystallising out. These are $2CaO.ZrO_2.4SiO_2$, $6SrO.ZrO_2.5SiO_2$, $CaSiO_3$, $SrSiO_3$ and SiO_2.

For those compositions studied all the ZrO_2 crystallises as $2CaO.ZrO_2.4SiO_2$ and $6SrO.ZrO_2.5SiO_2$ (if more ZrO_2 is present $ZrO_2.SiO_2$ will crystallise also). To fit the relative amounts of phases indicated by X-ray analysis the assumption has been made that the thermodynamics of formation of the $2CaO.ZrO_2.4SiO_2$ and $6SrO.ZrO_2.5SiO_2$ phases are very similar and that the distribution of ZrO_2 between these phases can be dealt with statistically. The relative ratios of these phases is then determined by the ratios of the CaO and SrO of the initial composition. The issue is further complicated by the fact that in these phases there are 2CaO's per ZrO_2 and 6SrO's per ZrO_2 respectively i.e. 3 times more SrO to CaO is required to form equal amounts of $2CaO.ZrO_2.4SiO_2$ and $6SrO.ZrO_2.5SiO_2$. Therefore to calculate how the ZrO_2 is split between $2CaO.ZrO_2.4SiO_2$ and $6SrO.ZrO_2.5SiO_2$ the applicants calculate the ratio of CaO/SrO and multiply by 3, because the CaO is 3 times more likely to form $2CaO.ZrO_2.4SiO_2$ than SrO is to form $6SrO.ZrO_2.5SiO_2$. The ZrO_2 content is divided by this figure to give the amount of $6SrO.ZrO_2.5SiO_2$ produced. The remaining ZrO_2 forms $2CaO.ZrO_2.4SiO_2$. (Of course if there is sufficient ZrO_2 to exhaust either the CaO or SrO the calculation must be modified accordingly). Now any remaining CaO forms $CaSiO_3$ and any remaining SrO forms $SrSiO_3$. The remaining excess SiO_2 can then be calculated.

With all these SrO containing compositions there will be inevitable discrepancies around the boundary areas. Small changes in the composition of only 0.1-0.2% are usually sufficient to be the difference between failure and pass at the boundary. In these systems there are considerable difficulties in analysing for SrO, CaO and SiO_2 together by X-ray fluorescence (XRF) because their XRF spectra interfere with each other thereby making it difficult to construct an accurate quantitative XRF programme for these systems. This means the accuracy of the reported compositions is less than would be expected for general XRF samples.

These factors may explain why two compositions (F29 and F16) in the $CaO-SrO-ZrO_2-SiO_2$ system show as failures when their excess SiO_2 figure would indicate them as being potentially useful fibres.

Under the heading "Comparative compositions" in Table 1 are shown two types of material. Those with the prefix "SCS" are compositions mentioned in WO/93/15028 as being potential refractory glass forming compositions. None of these fibres were made and as will be seen from the figures for excess SiO_2 given would not fall within the scope of the present application. The compositions shown with the prefix "BS" are fibres made containing appreciable amounts of both MgO and SrO and as can be seen these materials have an unsatisfactory shrinkage. Silica excesses have not been calculated for these compositions.

The applicants have looked to the various incidental impurities that can occur in inorganic oxide refractory fibres (e.g. alkali oxides and iron oxide) and have found that the impurity levels that can be tolerated vary according to the proportions of the main constituents of the fibre. Fibres containing high levels of ZrO_2 for example can tolerate higher levels of Na_2O or Fe_2O_3 than fibres with low levels of ZrO_2. Accordingly the applicants propose a maximum level of incidental impurities of 2mol%, the maximum level that will be tolerable will however vary as mentioned above.

The following describes in detail the methods used to measure shrinkage and solubility.

Shrinkage was measured by proposed ISO standard ISO/TC33/SC2/N220 (equivalent to British Standard BS 1920, part 6,1986) with some modifications to account for small sample size. The method in summary comprises the manufacture of vacuum cast preforms, using 75g of fibre in 500cm³ of 0.2% starch solution, into a 120 x 65mm tool. Platinum pins (approximately 0.1-0.3mm diameter) were placed 100 x 45mm apart in the 4 corners. The

longest lengths (L1 & L2) and the diagonals (L3 & L4) were measured to an accuracy of ±5μm using a travelling microscope. The samples were placed in a furnace and ramped to a temperature 50°C below the test temperature at 400°C/hour and ramped at 120°C/hour for the last 50°C to test temperature and left for 24 hours. The shrinkage values are given as an average of the 4 measurements.

It should be noted that although this is a standard way of measuring shrinkage of fibre it has an inherent variability in that the finished density of the preform may vary depending on casting conditions. Further it should be noted that fibre blanket will usually have a higher shrinkage than a preform made of the same fibre. Accordingly the 3.5% figure mentioned in this specification is likely to translate as a higher shrinkage in finished blanket.

Solubility was measured by the following method.

The fibre was first chopped - 2.5 g of fibre (deshotted by hand) was liquidised with 250 cm^3 of distilled water in a domestic Moulinex (Trade Mark) food blender for 20 seconds. The suspension was then transferred to a 500 cm^3 plastic beaker and allowed to settle after which as much liquid as possible was decanted and the remaining liquid removed by drying in an oven at 110°C.

The solubility test apparatus comprised a shaking incubator water bath, and the test solution had the following composition:-

Compound	Name	Grams
NaCl	Sodium chloride	6.780
NH$_4$Cl	Ammonium chloride	0.540
NaHCO$_3$	Sodium bicarbonate	2.270
Na$_2$HPO$_4$.H$_2$O	Disodium hydrogen phosphate	0.170
Na$_3$C$_6$H$_5$O$_7$.2H$_2$O	Sodium citrate dihydrate	0.060
H$_2$NCH$_2$CO$_2$H	Glycine	0.450
H$_2$SO$_4$ s.g. 1.84	Sulphuric acid	0.050

The above materials were diluted to 1 litre with distilled water to form a physiological-like saline solution.

9

0.500 grams ± 0.0003 grams of chopped fibre was weighed into a plastic centrifuge tube and 25 cm³ of the above saline solution added. The fibre and saline solution was shaken well and inserted into the shaking incubator water bath maintained at body temperature (37°C ± 1°C). The shaker speed was set at 20 cycles/minute.

After the desired period (usually 5 hours or 24 hours) the centrifuge tube was removed and centrifuged at 4500 revs/minute for approximately 5 minutes. Supernatant liquid was then drawn off using a syringe and hypodermic needle. The needle was then removed from the syringe, air expelled from the syringe, and the liquid passed through a filter (0.45 micron cellulose nitrate membrane filter paper [WCN type from Whatman Labsales Limited]) into a clean plastic bottle. The liquid was then analysed by atomic absorption using a Thermo Jarrell Ash Smith - Hiefje II machine.

The operating conditions were as follows using a nitrous oxide and acetylene flame:-

ELEMENT	WAVELENGTH (nm)	BAND WIDTH	CURRENT (mA)	FLAME
Al	309.3	1.0	8	Fuel Rich
SiO_2	251.6	0.3	12	Fuel Rich
CaO	422.7	1.0	7	Fuel Lean
MgO	285.2	1.0	3	Fuel Lean
SrO	460.7	0	12	Fuel Lean

The procedure and standards adopted for determining the above elements were as set out below.

SiO_2 can be determined without dilution up to 250 ppm concentration (1 ppm 1mg/Litre). Above this concentration an appropriate dilution was made volumetrically. A 0.1% KCl solution (0.1g in 100 cm³) was added to the final dilution to prevent ionic interference. NB If glass apparatus is used, prompt analysis is necessary.

From a stock solution of 1000 ppm pure ignited silica (99.999%) (fused with Na_2CO_3 at 1200°C for 20 minutes in a platinum crucible (0.2500g SiO_2/2g Na_2CO_3) and dissolved in dilute hydrochloric acid (4 molar) made up to 250cm³ with distilled water in a plastic volumetric flask) the following standards were produced:-

STANDARD (ppm SiO$_2$)	STOCK SOLUTION (cm^3)
10.0	1.0
20.0	2.0
30.0	3.0
50.0	5.0
100.0	10.0
250.0	25.0

Add 0.1% KCl to each standard before making to 100cm^3.

Aluminium may be measured directly from the sample without dilution. Standards of 1.0, 5.0 and 10.0 ppm Al may be used. For calibration readings are multiplied by 1.8895 to convert from Al to Al$_2$O$_3$.

A standard Al atomic absorption solution (e.g. BDH 1000 ppm Al) was bought and diluted using an accurate pipette to the desired concentration. 0.1% KCl was added to prevent ionic interference.

Calcium may require dilutions on the sample before determination can be carried out (i.e. x 10 and x 20 dilutions). Dilutions must contain 0.1% KCl.

A standard Ca atomic absorption solution (e.g. BDH 1000 ppm Ca) was diluted with distilled water and an accurate pipette to give standards of 0.5, 4.0 and 10.0 ppm. 0.1% KCl is added to prevent ionic interference. To convert readings obtained from Ca to CaO a factor of 1.4 was used.

Strontium is measured against a standard atomic absorption solution (Aldrich 970μm/ml). Three standards are prepared to which 0.1%KCl is added (Sr [ppm] 9.7,3.9 & 1.9). Dilutions of x10 and x20 are nromally made to measure Sr level in the sample. SrO is then calculated as 1.183xSr.

Magnesium may require dilutions on the sample before determinations can be made (i.e. x 10 and x 20). Add 0.1% KCl to each dilution. To convert Mg to MgO multiply by 1.658.

A standard Mg atomic absorption solution (e.g. BDH 1000 ppm Mg) was diluted with distilled water and an accurate pipette to give standards of 0.5, 1.0 and 10.0 ppm Mg. 0.1% KCl was added to prevent ionic interference.

All stock solutions were stored in plastic bottles.

The above has discussed resistance to shrinkage of preforms exposed to 1260°C for 24 hours. This is an indication of the maximum use temperature of a fibre. In practice fibres are quoted for a maximum continuous use temperature and a higher maximum exposure temperature. It is usual in industry when selecting a fibre for use at a given temperature to choose a fibre having a higher continuous use temperature than that nominally required for the intended use. This is so that any accidental increase in temperature does not damage the fibres. It is quite usual for a margin of 100 to 150°C to be given. Accordingly this invention extends to use of the claimed fibres at elevated temperatures (i.e. at temperatures where the refractoriness of fibres is important) and not just to use at 1260°C.

It will be evident that incidental impurity levels are preferably kept as low as possible. The applicants surmise that as the various crystalline materials crystallise from the fibres impurities migrate to the grain boundaries and concentrate there. Thus a small impurity can have a very large effect.

TABLE 1

CaO-SrO-ZrO2-SiO2 System

Comp.	Shrinkage: 800°	1000°	1200°	1300°	Composition (wt) CaO	MgO	SrO	ZrO2	Al2O3 (mol%)	TiO2	SiO2	SiO2	SrO.ZrO2.2SiO2	2CaO.ZrO2.4SiO2	6SrO.ZrO2.5SiO2	2CaO.ZrO2.5SiO2	CaSiO3	SrSiO3	Excess SiO2
F33	1.30	8.20			30.2	0.9	2.6	5	0.2		0.1	60.9	None			4.86	0.14	20.49	1.74	18.53
F28	1.50	5.10			31.6	0.9	2.6	2.4	0.3		0.1	62.1	None			2.33	0.07	26.93	2.21	23.30
F15	0.40	7.70			27.7	0.9	2.8	5	0.1		0.1	63.4	None			4.83	0.17	18.04	1.79	23.41
F34	0.10	6.00			24.9	0.8	5.7	4.8	0.2		0.1	63.6	None			4.43	0.37	16.03	3.50	24.50
F20		1.40	1.90	2.50	25.8	0.8	2.7	5.4	0.1		0.1	65.2	None			5.21	0.19	16.38	1.67	26.47
F1	1.10	1.50		2.30	29.4	0.9	2.7	2.5	0.1			64.3	None			2.42	0.08	24.65	2.24	27.43
F29		2.60		5.80	26.6	0.8	5.5	2.5	0.2		0.1	64.4	None			2.33	0.17	21.94	4.47	27.62
F18	0.40	4.20	6.10		22.7	0.8	5.7	5.2	0.1			65.4	None			4.76	0.44	13.17	3.09	27.91
F6	0.50	0.70	1.60	1.80	27.3	0.8	2.6	2.5	0.1		0.1	66.6	None			2.42	0.08	22.46	2.12	31.94
F2	0.80	1.10		2.80	24.3	0.6	5.7	2.5	0.1		0.1	66.7	None			2.30	0.20	19.69	4.53	32.29
F24		0.50	1.10	1.50	23.2	0.8	2.7	5.2	0.1		0.1	68	None			6.00	0.20	13.20	1.49	32.31
F21		0.60	1.60	2.70	20.2	0.8	5.7	5.4	0.1		0.1	67.7	None			4.89	0.51	10.42	2.65	32.52
F11	-0.10	0.30	0.80	1.40	25.3	0.8	2.9	2.4	0.1		0.1	68.4	None			2.31	0.09	20.98	2.35	35.68
F7	0.30	0.70	1.30	1.80	22.3	0.6	5.6	2.6	0.1		0.1	68.8	None			2.38	0.22	17.64	4.29	36.35
F3	0.30	0.70		2.50	18.8	0.5	8.8	2.7	0.1		0.1	69	None			2.28	0.42	14.24	6.27	37.28
F26		0.40	0.80	1.10	17.7	0.7	8.8	5.3	0.1		0.1	70.6	None			4.74	0.66	8.22	2.25	38.38
F12	-0.20	0.50	0.60	1.00	19.6	0.8	5.6	2.6	0.1		0.1	71.3	None			2.95	0.25	14.90	4.11	41.64

TABLE 1

CaO-SrO-SiO2 System

Comp.	Shrinkage 800C	1000C	1200C	1260C	Composition mol% CaO	MgO	SrO	ZrO2	Al2O3	TiO2	SiO2	SrO.ZrO2.2SiO2	2CaO.ZrO2.4SiO2	6SrO.ZrO2.5SiO2	CaSiO3	SrSiO3	Excess SiO2	CaSiO3/SrSiO3 ratio
E29	2.20	3.90	4.00	5.70	23.3	0.6	11.8				64	None	None	None	23.33	11.81	28.86	1.98
E30	1.20	2.60	1.90	4.70	17.8	0.5	15.2	0.1	0.2		66.2	None	None	None	17.77	15.17	33.28	1.17
E19	0.80	1.20		1.70	20	0.8	12	0.1	0.3	0.1	66.9	None	None	None	20.04	12.05	34.81	1.66
E4	0.40	1.40	1.10	0.60	19	0.5	11.5	0.2	0.1		68.7	None	None	None	18.98	11.47	38.25	1.65
E20	0.30	1.00		1.20	14.8	0.7	15.5	0.1	0.3	0.1	68.6	None	None	None	14.78	15.48	38.35	0.95
E5	0.30	0.40		0.80	12.9	0.3	15.5	0.1	0.1		71	None	None	None	12.93	16.47	42.61	0.84
E28	1.50	1.20		4.90	38.2	1	2.6		0.2	0.1	57.9	None	None	None	38.25	2.64	17.02	14.50
E27	1.30	2.00	4.90	7.90	33.8	0.9	5.6		0.2		59.5	None	None	None	33.76	5.57	20.17	6.06
E16	1.10	1.70	5.10	3.50	36.2	0.9	2.6		0.2		60	None	None	None	38.22	2.64	21.14	13.74
E28	2.80	5.70		7.90	28.6	0.8	8.2		0.3	0.1	62.1	None	None	None	28.57	8.19	25.34	3.49
E17	0.80	1.00	2.30	2.80	30.1	0.8	5.7		0.2		63.2	None	None	None	30.11	8.65	27.44	5.33
E6	0.50	0.70		0.20	32	0.8	2.6		0.2		64.2	None	None	None	32.01	2.65	28.64	12.09
E1	0.90	1.00		1.70	31.9	0.8	2.6		0.3	0.1	64.4	None	None	None	31.85	2.65	29.90	12.03
E18	0.70	1.40	1.30	1.40	25.3	0.8	8.8	0.1	0.2		65	None	None	None	25.28	8.77	30.96	2.88
E2		1.00		2.50	27.4	0.8	5.4	0.1	0.2		66.1	None	None	None	27.41	5.41	33.28	5.07
E7		0.60		0.80	26.9	0.6	5.7		0.2	0.1	66.5	None	None	None	26.94	5.41	33.89	4.75
E11	0.20	0.70	1.30	0.80	29.7	0.7	2.6	0.1	0.2	0.1	66.6	None	None	None	29.70	8.67	34.26	11.25
E3	0.60	1.00	1.50	1.50	22.4	0.6	8.3	0.2	0.1	0.1	68.4	None	None	None	22.37	2.64	37.69	2.68
E12	0.20	0.60		0.90	23.5	0.6	5.7		0.4	0.1	69.7	None	None	None	23.55	8.65	40.60	4.17

Comparative compositions

Comp.	Shrinkage 800C	1000C	1200C	1260C	Composition mol% CaO	MgO	SrO	ZrO2	Al2O3	TiO2	SiO2	SrO.ZrO2.2SiO2	2CaO.ZrO2.4SiO2	6SrO.ZrO2.5SiO2	CaSiO3	SrSiO3	Excess SiO2	CaSiO3/SrSiO3 ratio
SCS(A)					22.4		25.7				51.9	None	None	None	29.70	2.64	19.56	11.25
SCS(C)					35		12.6				52.4	None	None	None	22.37	8.34	21.69	2.68
SCS(B)					11.1		38.1				50.8	None	None	None	23.55	5.65	21.60	4.17
BS-2	0.60	1.30		7.50	9.6	18.2		0.1	0.1	0.1	66.6							
BS-1		1.30		3.90	14.4	17.8		0.3	0.2	0.1	64.8							
BS-4	0.40	1.30		12.50	9.8	14.8		2.9	0.1	0.1	67		Not calculated					
BS-3	0.20	1.20		4.50	14	14.4		2.8	0.1	0.1	66.2							
BS-5	0.20	1.20		12.90	14.3	13.3		0.3	0.1	0.1	66.7							
BS-6	0.50	1.10		23.00	13.2	11.9		2.7	0.1	0.1	66.8							

TABLE 2

CaO-SrO-ZrO2-SiO2 System

| Comp. | Composition mol% | | | | | | | Solubility (ppm) | | | |
	CaO	MgO	SrO	ZrO2	Al2O3	TiO2	SiO2	CaO	MgO/SrO	SiO2	Total
F33	30.2	0.9	2.6	5	0.2	0.1	60.9	22	12	29	63.00
F28	31.6	0.9	2.6	2.4	0.3	0.1	62.1	43	16	78	137.00
F15	27.7	0.9	2.8	5	0.1	0.1	63.4	17	11	22	50.00
F34	24.9	0.8	5.7	4.8	0.2	0.1	63.6	19	14	27	60.00
F20	25.8	0.8	2.7	5.4	0.1	0.1	65.2	11	10	15	36.00
F1	29.4	0.9	2.7	2.5	0.1	0.1	64.3	32	14	60	106.00
F29	26.6	0.8	5.5	2.5	0.2		64.4				
F16	22.7	0.8	5.7	5.2	0.1	0.1	65.4	15	12	17	44.00
F6	27.3	0.8	2.6	2.5	0.1	0.1	66.6	30	12	53	95.00
F2	24.3	0.6	5.7	2.5	0.1	0.1	66.7	24	17	48	89.00
F24	23.2	0.8	2.7	5.2	0.1	0.1	68	11	10	17	38.00
F21	20.2	0.8	5.7	5.4	0.1	0.1	67.7	10	12	14	36.00
F11	25.3	0.8	2.9	2.4	0.1	0.1	68.4	20	12	31	63.00
F7	22.3	0.6	5.6	2.6	0.1	0.1	68.8	25	19	43	87.00
F3	18.8	0.5	8.8	2.7	0.1	0.1	69	8	14	32	54.00
F25	17.7	0.7	5.6	5.3	0.1	0.1	70.6	13	12	19	44.00
F12	19.6	0.8	5.6	2.6	0.1	0.1	71.3	19	17	33	69.00

CaO-SrO-SiO2 System

| Comp. | Composition mol% | | | | | | | Solubility (ppm) | | | |
	CaO	MgO	SrO	ZrO2	Al2O3	TiO2	SiO2	CaO	MgO/SrO	SiO2	Total
E29	23.3	0.6	11.8		0.2		64	33	47	103	183.00
E30	17.8	0.5	15.2	0.1	0.2	0.1	66.2	23	54	92	169.00
E19	20	0.6	12	0.1	0.3		66.9	32	52	88	172.00
E4	19	0.5	11.5	0.2	0.1	0.1	68.7	32	50	69	151.00
E20	14.8	0.7	15.5	0.1	0.3		68.6	20	53	59	132.00
E5	12.9	0.3	15.5	0.1	0.1	0.1	71	21	66	54	141.00
E26	38.2	1	2.6		0.2		57.9				
E27	33.8	0.9	5.6		0.2		59.5	57	30	148	235.00
E16	38.2	0.9	2.6		0.2	0.1	60.	61	13	137	211.00
E28	28.6	0.9	8.2		0.2		62.1	50	44	152	246.00
E17	30.1	0.8	5.7		0.3		63.2	54	27	115	196.00
E6	32	0.9	2.6		0.2		64.2	61	16	100	177.00
E1	31.9	0.8	2.6		0.2	0.1	64.4	71	17	120	208.00
E18	25.3	0.6	8.8	0.1	0.3		65	39	37	90	166.00
E2	27.4	0.8	5.4	0.1	0.2	0.1	66.1	62	32	113	207.00
E7	26.9	0.6	5.7		0.2	0.1	66.5	54	34	90	178.00
E11	29.7	0.7	2.6		0.2	0.1	66.6	50	12	90	152.00
E3	22.4	0.6	8.3	0.1	0.1	0.1	68.4	44	41	84	169.00
E12	23.5	0.6	5.7	0.2	0.4		69.7	44	31	87	162.00

CLAIMS

1. A refractory fibre for which a vacuum cast preform of the fibre has a
    shrinkage of 3.5% or less when exposed to 1260°C for 24 hours and
    comprising CaO, SiO_2, SrO, and optionally ZrO_2 any incidental impurities
    amounting to less than 2mol% in total, and in which the SiO_2 excess
    (defined as the amount of SiO_2 calculated as remaining after the above
    named constituents are crystallised as silicates) exceeds 26mol%

2. A refractory fibre as claimed in claim 1 and comprising:-
    CaO   less than 33.8 mol%
    SiO_2 more than 62.1 mol%.

3. A refractory fibre as claimed in claim 2 and comprising:-
    CaO   12.9 to 31.9 mol%
    SrO   2.6 to 15.5 mol%
    SiO_2 63.2 to 71.3 mol%
    ZrO_2 0 to 5.4 mol %.

4. A method of providing a saline soluble refractory fibre for use at elevated
    temperatures comprising selecting a fibre as claimed in any of claims 1 to
    3.

INTERNATIONAL SEARCH REPORT

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6   C03C13/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6   C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,4 036 654 (B.YALE ET AL.) 19 July 1977 see column 1, line 10 - column 2, line 13 ---	1-4
A	CHEMICAL ABSTRACTS, vol. 115, no. 26, 30 December 1991 Columbus, Ohio, US; abstract no. 285711, page 366; see abstract & DD,A,293 105 (AKADEMIE DER WISSENSCHAFTEN) 22 August 1991 ---	1-4
	-/--	

[X] Further documents are listed in the continuation of box C.	[X] Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
4 October 1995	26. 10. 95

Name and mailing address of the ISA	Authorized officer
European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Reedijk, A

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DATABASE WPI Week 7038 Derwent Publications Ltd., London, GB; AN 70-69235 & SU,A,259 337 (GEN AND ORG CHEM INST ACA) , 1970 see abstract -----	1-4

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
US-A-4036654	19-07-77	GB-A-	1399556	02-07-75
		AU-B-	6357273	19-06-75
		BE-A-	808744	17-06-74
		CA-A-	985710	16-03-76
		DE-A-	2361195	11-07-74
		FR-A,B	2210579	12-07-74
		JP-C-	1118328	15-10-82
		JP-A-	49099311	19-09-74
		JP-B-	57008777	18-02-82
		LU-A-	69010	22-02-74
		NL-A-	7317097	21-06-74
		SE-C-	392458	07-07-77